



Brayco 717

Fluid, Power Transmission

Description

Castrol Brayco™ 717 is a straw-colored, medium viscosity hydraulic fluid. It is a blend of highly refined petroleum basestocks and additives, which provide resistance to oxidation and corrosion, anti-wear properties and a high viscosity index.

Application

Brayco 717 is designed for the hydraulic transmission of power in Naval ordinance hydraulic equipment. It provides corrosion protection in the presence of salt water and spray.

It can be used over an operating temperature range of -40°C to 122°C (-40°F to 250°F) and meets the requirements of military specification MIL-DTL-17111E which requires first article testing rather than formal qualification and approval.

This fluid is identified by NATO Code Number H-575.

Typical Characteristics

Name	Method	Units	MIL-DTL-17111E specification	Brayco 717
Base fluid				
Acid Number	ASTM D 974	mg KOH/g	0.05 max.	0.01
Aniline Point change	ASTM D 611	°C	2.8 max.	0.6
Precipitation Number	ASTM D 91	-	0.05 max.	0.02
Aniline Point	ASTM D 611	°C	77 min.	83.4
Finished Product				
API Gravity	ASTM D 287	-	30-33 typical	30.9
Specific Gravity @ 15°C / 59°F	ASTM D 1298	-	0.859-0.875 typical	0.871
Density @ 15°C / 59°F	ASTM D 4052	lbs/gal	-	7.25
Kinematic Viscosity @ -35°C / -31°F	ASTM D 445	mm ² /s	1000 max.	828
Kinematic Viscosity @ -20°C / -4°F	ASTM D 445	mm ² /s	500 max.	278
Kinematic Viscosity @ 40°C / 104°F	ASTM D 445	mm ² /s	25 min.	26.4
Kinematic Viscosity @ 100°C / 212°F	ASTM D 445	mm ² /s	8 min.	8.8
Flash Point - open cup method	ASTM D 92	°C/°F	104 / 220 min.	110 / 230
Fire Point	ASTM D 92	°C/°F	113 / 235 min.	118 / 245
Acid Number	ASTM D 974	mg KOH/g	0.3 max.	0.1
Precipitation Number	ASTM D 91	-	0.05 max.	0
Water Content - Dean-Stark distillation test	ASTM D 95	% wt	0.0 max.	0
Color	ASTM D 1500	-	2 max.	<1
Low Temperature Turbidity (72 hrs @ -37°C / -35°F)	MIL-DTL-17111E spec 4.5.3.2	Pass	Pass	Pass
Rust test - distilled water (24 hrs)	ASTM D 665A	-	Pass	Pass
Corrosion & Oxidation Stability - 72 hrs @ 93.3°C / 201°F:				
Change in Viscosity @ 100°C / 212°F	MIL-DTL-17111E spec 4.5.3.4.2	%	0 to 15	4.4
Change in Viscosity @ -20°C / -4°F		%	0 to 15	24.5
Acid Number - Oil Layer		mg KOH/g	0.5 max.	0.08
Acid Number - Water Layer		mg KOH/g	0.5 max.	0
Loss of liquid		g	10 max.	2.6
Evaporation Loss	ASTM D 972	% wt	20 max.	7.1
Water Sludging tendency @ 38°C	MIL-DTL-17111E spec 4.5.3.5	% Viscosity change	-2 to 10	8.1
Workmanship	MIL-DTL-17111E spec 3.2.5	Pass	Pass	Pass

Subject to usual manufacturing tolerances.

Brayco 717
02 Nov 2012
Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, North America Inc., 150 West Warrenville Road, 603 1E Naperville, IL 60563
Tel: (877) 641 1600 Fax: (877) 648 9801
www.castrol.com/industrial