

**Product Data** 

## **Brayco Micronic 883**

Specialized Synthetic Hydraulic Fluid

## **Description**

Castrol Brayco™ Micronic 883 is a rust-inhibited fire resistant synthetic ISO viscosity Grade 15 hydraulic fluid for aircraft, ordnance and industrial use. It contains no viscosity index improvers and therefore, unlike conventional hydraulic fluids, it is not subject to polymeric breakdown. This product is compatible with MIL-H-5606G and MIL PRF- 6083F in all proportions.

## **Application**

Brayco Micronic 883 is primarily designed as a fire resistant hydraulic fluid with superior corrosion resistance. MIL-PRF-46170C is intended for use as a direct replacement for MIL-PRF-6083.

Brayco Micronic 883 meets and is qualified under military specification MIL-PRF-46170C, Type I, Amendment 2.

## **Typical Characteristics**

| Name   | Method                     | Units    | 883     |
|--|----------------------------|----------|---------|
| Specific Gravity @ 15.6°C                            | VN-TM-005 (ASTM D-<br>287) | -        | 0.85    |
| Pounds per Gallon                                    | Table 8 (VN-TM-005)        | -        | 7.08    |
| Kinematic Viscosity @ 204°C / 400°F                  | ISO 3104 / ASTM D 445      | mm²/s    | 1.15    |
| Kinematic Viscosity @ 100°C / 212°F                  | ISO 3104 / ASTM D 445      | mm²/s    | 3.7     |
| Kinematic Viscosity @ 40°C / 104°F                   | ISO 3104 / ASTM D 445      | mm²/s    | 15.6    |
| Kinematic Viscosity @ -40°C / -40°F                  | ISO 3104 / ASTM D 445      | mm²/s    | 2450    |
| Kinematic Viscosity @ -54°C / 65°F                   | ISO 3104 / ASTM D 445      | mm²/s    | 14650   |
| Viscosity Index                                      | ISO 2909 / ASTM D2270      | -        | 126     |
| Flash Point, COC                                     | ISO 2592 / ASTM D92        | °C/°F    | 226/440 |
| Fire Point, COC                                      | ISO 2592 / ASTM D92        | °C/°F    | 252/485 |
| Sediment, Trace                                      | ASTM D2273                 | % vol    | 0.001   |
| Pour Point   | ISO 2592 / ASTM D92        | °C/°F    | -60/-75 |
| Water Content  | ISO 6296 / ASTM D1744      | %        | 0.02    |
| Acid Number  | ISO 6619 / ASTM D664       | mg KOH/g | 0.04    |
| Autoignition Temperature                             | ASTM E659                  | °C/°F    | 380/716 |
| Low Temperature Stability @ -40°C/-40°F for 72 hours | FTM 3458                   | -        | Pass    |
| Rust Prevention (polished/sandblasted panels)        | ASTM D1748                 | -        | Pass    |
| Rubber Swell, "L" 168 hrs @ 70 Deg C                 | ASTM D4289                 | %        | 17      |

| Name  | Mada al              | 11-14-            | 000   |
|---|----------------------|-------------------|---|
| Name  | Method               | Units             | 883   |
| Foam Sequence I - tendency / stability  | ISO 6247 / ASTM D892 | ml/ml             | 10/0  |
| Foam Sequence II - tendency / stability   | ISO 6247 / ASTM D892 | ml/ml             | 10/0  |
| Foam Sequence III - tendency / stability  | ISO 6247 / ASTM D892 | ml/ml             | 10/0  |
| Four Ball Wear, 1200 rpm, 1hr, 75°C<br>@10 kgf<br>@40 kgf   | ASTM D 4172          | mm Scar           | 0.25<br>0.45  |
| Particle Count automatic, 5-25 micron   | VN-TM-013            | Per 100ml         | 4000  |
| Particle Count automatic, 25-50 micron  | VN-TM-013            | Per 100ml         | 36  |
| Particle Count automatic, 50-100 micron   | VN-TM-013            | Per 100ml         | 4   |
| Particle Count automatic, >100 micron   | VN-TM-013            | Per 100ml         | 1   |
| Oxidation and Corrosion Stability 168 hrs, 121°C (250°F), weight change Copper Magnesium Aluminium Steel Viscosity Change Change in acid number | FTM 3009             | mg/cm²  % mgKOH/g | -0.1<br>0<br>0<br>0<br>2.5<br>0.05                  |
| Bulk Modulus, Isothermal Secant. 0 to 10,000 psi @ 37.8°C (100°F), 2000<br>4000<br>6000<br>8000<br>10000  | -                    | minutes           | 206,000<br>219,000<br>234,000<br>240,000<br>262,000 |

Subject to usual manufacturing tolerances.

Brayco Micronic 883 19 Sep 2013

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

 $Castrol\ Industrial, Technology\ Centre\ ,\ Whitchurch\ Hill\ ,\ Pangbourne\ ,\ Reading\ ,\ RG8\ 7QR\ ,\ United\ Kingdom$ 

www.castrol.com/industrial