



Castrol Braycote 236

Technical Grade Petrolatum

Description

Castrol Braycote™ 236 is a soft, reddish-brown grease-like technical grade petrolatum. It forms a soft, translucent, flexible coating on parts to which it is applied, and is readily removed with solvent or by steam cleaning processes.

Application

Braycote 236 is intended for use as a light grade of lubricating grease, but is not recommended for use in heavily loaded or hot running bearings. It may be used as a constituent in petrolatum base rust preventive compounds.

Typical Characteristics

TEST METHOD	DESCRIPTION	VV-P-236A REQUIREMENTS	RESULT
D 1500	Color, ASTM	2-8	<3.0
D 127	Melting Point, °F (°C)	115-140 (46-60)	133 (56)
D 92	Flash Point, COC, °F (°C)	390 (198) Minimum	480 (248)
D 937	Penetration, Unworked, mm/10	150 - 275	194
FTM 5309	Corrosion on Copper, 24 hours, 100°C (212°F)	None	None
D 482	Ash Content, %	0.1 Maximum	0.01
D 974	Neutralization Number, mg KOH/g	0.1 Maximum	0.014
D 91	Precipitation Number	0.10 Maximum	0.005
Spec	Abrasive Material	None	None
Spec	Evaporation Loss 1 hour, 107°C (225°F), % wt	2 Maximum	0.1
D 97	Pour Point, °F (°C)	Report	130 (54)
D 445	Viscosity @ 100°C (212°F), cSt	11.6-18.0	13

Subject to usual manufacturing tolerances.

Additional Information

Specification

Braycote 236 meets the requirements of Federal Specification VV-P-236A.

Castrol, Braycote, and the Castrol logo are trademarks of Castrol Limited, used under licence

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, UK
www.castrol.com/industrial
www.castrol.com/industrial