



Braycote 622

Grease, General Purpose

Description

Castrol Braycote™ 622 is a synthetic hydrocarbon base, non-soap thickened grease. It offers outstanding high and low temperature properties, water resistance, and extreme pressure characteristics making it suitable for applications that exceed the capabilities of the best conventional greases. Braycote 622 has good oxidation and corrosion resistance, low bleed and evaporation rate, and minimal effect on rubber seals. Its compatibility with mineral oil base greases is an added advantage.

Application

Braycote 622 is particularly suited for aircraft applications such as wheel bearings, helicopter rotor bearings, control systems, applications including conveyor bearings, small alternator bearings operating at temperatures near 350°F (177°C), high speed miniature ball bearings, and bearing situations where oscillation, vibration, and fretting create problems.

Typical Characteristics

Name	Method	Units	
Penetration @ 25°C (77°F) mm-1 worked 60 strokes	D 217	281	
Worked stability, penetration, mm-1, 100,000 @ 25°C (77°F)	FTM 313	315	
Dropping Point, °C (°F)	D 2265	275 (>500)	
Copper strip corrosion, 24hrs @ 100°C (212°F)	FTM 5309	1a	
Evaporation Loss, % wt 22hrs @ 176°C (349°F)	D 2595	4.34	
Four-ball wear test, AWSD, mm 1200 rpm, 40 kgf, 1 hr @ 75°C (167°F)	D 2266	0.62	
Four-ball extreme pressure weld, kgf	D 2596	45	
Low-temperature torque, N.m @ -54°C (-65°F) starting, running 1hr	D 1478	0.32, 0.05	
Particulate contamination per mL, 25-74 microns	FTM 3005	72	
Water washout @ 38°C % loss	D 1264	>1	
Oil separation, 30 hours @ 350°F, % wt	F 321	>6	
Specific gravity @ 16°C (60°F), pounds per gallon @ 16°C (60°F)	D 287	0.882, 7.34	

Subject to usual manufacturing tolerances.

Additional Information

Temperature Range

Braycote 622 is designed to operate over the temperature range of -54°C to 177°C (-65°F to 350°F).

Specification Castrol

Braycote® 622 meets all the requirements of, and is qualified under military specification MIL-PRF-81322G, NLGI Grade 2 and DOD-G-24508A, Amendment 4 (NAVY).

Braycote 622

01 Jul 2013

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial , North America Inc. , 150 West Warrenville Road , 603 1E Naperville , IL 60563
Tel: (877) 641 1600 Fax: (877) 648 9801
www.castrol.com/industrial